

Client: J Bradbury & Co Ltd
Britannia Mills
Crosland Moor
Huddersfield
HD1 4TW

Entry No: 69319

Date received: 02/03/2015

Client's Description: Sample of fabric: 289322 Pyra

TEST REPORT

Test Required: Flammability

Pre-treatment: None

Conditioning: A minimum of 24 hours at 50 +/- 5% Relative Humidity, 23 +/- 2°C

Method of Test: BS EN 1021-1:2006 – smouldering cigarette
BS EN 1021-2:2006 – match flame equivalent

Date of Test: 02/04/2015

Ignition Source	Observations	Result
Smouldering cigarette	No flaming or progressive smouldering was observed within one hour of placement of the cigarettes.	PASS
Match flame equivalent	Flaming ceased within the specified two minute period after removal of the butane flame and no progressive smouldering occurred.	PASS


Note: A 35 kg/m³ CM foam (Carpenters RX36-125) was used as the filling

The above tests relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use.

-----End of Document-----

This is hereby certified to be a correct return of the tests made of the items referred to herein.



- 
- D. Brockbank.
Materials Testing Manager
13th May 2015
- ❖ Unless instructed otherwise by the client sample remnants will be disposed of after 28 days
 - ❖ Test marked (*) in this certificate are not included in the UKAS Accreditation Schedule for this Laboratory.
 - ❖ Opinions and interpretations expressed herein are outside the scope of UKAS accreditation.
 - ❖ This Certificate relates only to the sample received and, unless that sample has been drawn by the staff of this laboratory, or its agent, and endorsed accordingly, any application of the result to a bulk quantity or other material is entirely the responsibility of the client.

